

Technical Data Sheet

Ultrasint TPU® 88A black

Technical Data Sheet for Ultrasint TPU® 88A black

Version No.: 1.1, revised 01/2022

General information

Components

Thermoplastic polyurethane powder for Laser Sintering

Product Description

Ultrasint® TPU 88A black is a multi-purpose material for application in Laser Sintering. Parts produced with this material offer a balanced property profile with good flexibility, shock absorption and the possibility to print very fine structures with a high level of detail. In addition, the material is easy to print, and has good UV and hydrolysis resistance. This material is also suitable for desktop machines.

Typical applications are:

- Sports & Leisure
- Footwear
- Transportation Industry
- Jigs & Fixtures

Delivery Form & Warehousing

Ultrasint TPU® 88A black should be stored at 15 – 35°C in its originally sealed package in a clean and dry environment.

Product safety

Mandatory and recommended industrial hygiene procedures and the relevant industrial safety precautions must be followed whenever this product is being handled and processed. Product is sensitive to humid environment conditions. For additional information please consult the corresponding material safety data sheets.

For your Information

Ultrasint TPU® 88A black comes in black color. Chemical properties (e.g. resistance against particular substances) and tolerance for solvents are available upon request. Generally, these properties correspond to publicly available data on polyurethanes.

Notice

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

The safety data given in this publication is for information purposes only and does not constitute a legally binding Material Safety Data Sheet (MSDS). The relevant MSDS can be obtained upon request from your supplier or you may contact Forward AM directly at sales@basf-3dps.com.

Technical Data Sheet for Ultrasint TPU® 88A black

Version No.: 1.1, revised 01/2022

| General Properties | Test Method | Typical Values |
|--|----------------------|----------------|
| Bulk Density / g/cm ³ | DIN EN ISO 60 | 0.5 |
| Printed Part Density / g/cm ³ | DIN EN ISO 1183-1 | 1.1 |
| Mean Particle Size d50 / μm | ISO 13320 | 70-90 |
| Glass Transition Temperature / °C | ISO 11357 (20 K/min) | - 48 |
| Melting Temperature / °C | ISO 11357 (20 K/min) | 120-150 |

| Thermal Properties | Test Method | Typical Values ¹ X-Direction |
|---------------------|----------------|--|
| Vicat/A (10 N) / °C | DIN EN ISO 306 | 101.7 |

| Mechanical Properties | Test Method | Typical Values ¹ X-Direction | Typical Values ¹ Z-Direction |
|---|------------------|--|--|
| Hardness Shore A | DIN ISO 7619-1 | 86-88 | 86-88 |
| Tensile Strength / MPa | DIN 53504, S2 | 8 | 5 |
| Tensile Elongation at break / % | DIN 53504, S2 | 360 | 100 |
| Tensile Modulus / MPa | ISO 527-2, 1A | 85 | 85 |
| Rebound Resilience / % | DIN 53512 | 63 | 64 |
| Abrasion Resistance / mm ³ | DIN ISO 4649 | 121 | 123 |
| Charpy Impact Strength (notched, -30°C) / kJ/m ² | DIN EN ISO 179-1 | No break | No break |
| Fatigue Behavior (Rossflex, 100k cycles, 23°C) | ASTM D1052 | No cut growth | |
| Compression Set B (23°, 72h) / % | DIN ISO 815-1 | 24 | 28 |

 Detailed material data and support for FEA simulations available on request (sales@basf-3dps.com).

1) Measured after conditioning 3 days at 23°C and 50% r.h.

All values represent the stable part performance obtained when using the recommended refresh rate of 20% fresh + 80% recycled powder.


 12 rue Jean Bart
 78960 Voisins le Bretonneux

 Tel: + 33 (0)1 30 60 03 33
 Email: devis@3dsolutions.fr
www.3dsolutions.fr